

	Units	WeatherTrek™ EVD
THICKNESS*	microns	80
	mils	3.2
BASIS WEIGHT*	lbs/msf	14.5
	sq.in/lb	9,930
TENSILE STRENGTH* (ASTM D-882)	lbs/inch MD	27
	lbs/inch CD	24
TEAR RESISTANCE*	grams	2,500
AIR POROSITY* (TAPPI T-460)	sec/100cc	8.1
MVTR* (ASTM E-96A)	gm/100in ² /24hrs.	6.5 perms
WATER RESISTANCE* (ASTM D-779)		Pass
SURFACE BURNING CHARACTERISTICS* (ASTM E-84-97a)	Flame Spread	class A
	Indexed Smoke Developed Value	class A
USE TEMPERATURE*		200° F Maximum, -70° F Minimum
UV EXPOSURE RATING*	Days	365

*Note: Specifications listed are based on the performance of Valeron® Film, National Evaluation Report No. 494, Sept. 1, 2002. The information contained in this data sheet is to the best of our knowledge, true and accurate and is presented in good faith. Ludlow Coated Products assumes no liability, expressed or implied as to the architecture, engineering, or workmanship of any project. This information may be concurrent with, or superseded by other applicable documents. Contact Ludlow Coated Products for further information or technical support, contact Ludlow Coated Products at 877.832.0333.

tyco

Plastics &
Adhesives

**Ludlow Coated
Products**

Ludlow Coated Products
400 Texas Street, Suite 1150
Shreveport, LA 71101

T. 877.832.0333
www.ludlowcp.com



“As part of the
Ludlow Moisture
Management
Program for
Sound Building
Practices”